

ENVERTEK SLOPE 70

TECHNICAL DATA SHEET | NOVEMBER 2024

PRODUCT DESCRIPTION

ENVERTEK SLOPE 70 are non-combustible, mono density, hydrophobic thermo insulation boards with a disturbed fiber arrangement, made of stone wool, with a 2 % standard gradient.

APPLICATION

Thermal and non-combustible insulation in industrial and civil construction. Intended for use in construction facilities to create a positive drainage of water from rooftop areas and to avoid ponding. Part of a flat roof thermal insulation system.

FEATURES AND ADVANTAGES

- Non-combustible (A1)
- High compressive strength
- Dimensionally stable
- Vapor permeable
- Mono density
- Recyclable
- Thermal and sound insulation
- RAL and EUCEB certified
- CE marked (EN 13162)
- Thickness range 30 – 110 mm



DECLARED PARAMETERS

Parameter	Symbol	Unit	Level	Standard
Area of application	-	-	DAA	DIN 4108-10
Declared thermal conductivity	λ_D	W/mK	0.039	EN 13162
Declared thermal conductivity	λ_B	W/mK	0.040	DIN 4108-4
Thickness tolerance class	T	-	T4	EN 823
Dimensional stability under certain temperature and humidity conditions	DS(70,90)	%	≤1	EN 1604
Reaction to fire	RtF	-	A1	EN 13501-1
Short-term water absorption	WS	kg/m ²	≤1	EN 1609
Water vapor diffusion resistance coefficient	MU	-	MU1	EN 12086
Compressive stress at 10% deformation	CS(10)	kPa	70	EN 826
Point load at 5 mm deformation	PL(5)	N	800	EN 12430
Tensile strength perpendicular to the faces	TR	kPa	10	EN 1607

Product code: MW-EN 13162-T4-DS(70,90)-CS(10)70-TR10-PL(5)800-WS-MU1



Effective thermal insulation



Non-combustible



Noise reduction



Moisture resistant



Resistant to decay

ENVERTEK SLOPE 70

NOVEMBER 2024

DECLARED THERMAL RESISTANCE

Thickness (mm)	10	20	30	40	50	60	70	80	90	100	110	120	130	140	150
R _D (m ² K/W)	-	-	0.75	1.00	1.25	1.5	1.75	2.05	2.30	2.55	2.8	-	-	-	-
Thickness (mm)	160	170	180	190	200	210	220	230	240	250	260	270	280	290	300
R _D (m ² K/W)	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-

LOGISTICS INFORMATION

Full truck loading: 26 standard pallets

STORAGE

The product may only be stored outdoors in an intact, originally packed pallet. Protected against the harmful effects of weather conditions and set on a dry and stable surface. Maximum stacking height 3 pallets.

STANDARD DIMENSIONS AND PACKAGING

Thickness min (mm)	Thickness max (mm)	Length (mm)	Width (mm)	Pallet size (mm)	Pallet (m ³)	Pallet (m ²)	Slabs on a pallet (-)	Pallet height (on wood) (mm)
30	50	1000	1200	1000 x 1200	1.01	33.60	28	1250
50	70	1000	1200	1000 x 1200	1.08	21.60	18	1210
70	90	1000	1200	1000 x 1200	1.18	16.80	14	1250
90	110	1000	1200	1000 x 1200	1.30	14.40	12	1330

CERTIFICATION MARKS



HEALTH AND SAFETY

Kingspan rock mineral fibre insulation materials are declared as articles under the REACH Regulation (EC) No. 1907/2006. All components are not subject to classification and labelling requirements under the CLP Regulation (EC) No. 1272/2008.

For health and safety information please refer to Kingspan Mineral Insulation Safe Use Instruction Sheet.